

4207-1 Milgen Road, Columbus, GA 31907

Telephone: 844-309-6337

www.texttest.com

TexTesT Report: 11839
Date: 2/26/2021
Page: 1 of 1

CLIENT:

SOX EROSION SOLUTIONS

950 Peninsula Corp. Circle Suite 2020
Boca Raton, FL 33487

ATTN: Jake Shay

SAMPLE IDENTIFICATION: Type 2
2 layers

BREAKING STRENGTH & ELONGATION

ASTM D 5034

GRAB METHOD**Breaking Strength**

Machine Direction	135 lbf.
Cross Direction	207 lbf.

Elongation

Machine Direction	32.33 %
Cross Direction	61.7 %

TEAR STRENGTH**TRAPEZOID METHOD**

ASTM D 5587, Option 1

Average of Five Highest Peaks

Machine Direction	58.0 lbs.
Cross Direction	70.3 lbs.


BURSTING STRENGTH

ASTM D 3786

DIAPHRAGM METHOD

	275
	255
	305
	285
	280
	295
	285
	255
	310
	290
Average	284 psi

TEXTTEST



Signed by